



Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

RON MILLER AND/OR TERRY MILLER
PO BOX 280
50 The Great RD

Date: 5-Aug-20
Shear ID: 199869
Test No: 198311


Animal and Sample Description

Animal Name: SNOWSHOE PLEIONE
Registry #: 32653410
Breed: Huacaya
Sex: FEMALE
Colour: 100 - White

Date of Birth (Age): 12-Aug-14
Sample Location: GRID
Sample Date: 27-Apr-20
Previous Shear Date: 25-Apr-19
Total Fleece Wt (lbs): 0.00

Laboratory Data

Mean Fiber Diameter:	23.6 microns	Mean Staple Length:	70 mm
Standard Deviation:	3.5 microns	Length Standard Deviation:	3.6 mm
Coefficient of Variation:	14.6 %	Length Coefficient of Variation:	5.1 %
Spin Fineness:	21.9 microns	Mean Curvature:	47.1 deg/mm
Fibers Greater Than 30 microns:	3.6 %	SD Curvature:	26.4 deg/mm
Comfort Factor:	96.4 %	Medullated Fibers:	12.8 %



Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear
Business Manager

Jude Davidson
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilmorie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: nz.wool.timaru@sgs.com Web: www.wooltesting.sgs.com